

Fenochem Moulding Compound

C 3500 *Compression Grade*

Colour	:	black		
Reinforcement	:	wood flour/inorganic		
Application areas	:	for general purpose, easy to mould, suitable for the production of a wide range of articles		
Mark	:	DIN 31/1449		
PROPERTY		METHOD	UNIT	VALUE
Density		ISO 1183	g/cm ³	1.40
Mould. shrinkage		ISO 2577	%	0.6 - 0.8
Post- shrinkage		ISO 2577	%	0.4 - 0.6
Water absorption		ISO 62	mg	≤ 100
Flexural strenght		ISO 178	MPa	≥ 70
Charpy impact strenght		ISO 179	KJ/m ²	≥ 4.5
Charpy not. imp. strenght		ISO 179	KJ/m ²	≥ 1.3
Temper. of defl.under load		ISO 75	°C	≥ 115
Flammability (meth. BH)		IEC 707	CLASS	≤ BH 2 - 10
Surface resistance		IEC 93	Ohm	≥ 10 ⁸
Volume resistivity		IEC 93	Ohm • cm	≥ 10 ¹⁰
Proof-tracking index		IEC 112	V	≥ 125
				Rev. Febbruary_2010

The information given in our datasheet, which to our knowledge is correct, does not constitute any kind of warranty or other undertaking of responsibility from Chemiplastica, but serves only as general information with respect to possible applicability of the products as well as the characteristics and handling of the products.

